

DATASHEET

Quality; SPEYPACK® ECO

Origin; Europe

SPEYPACK ECO 655g/770um		DATA	TOLERANCE
Grammage	g/m ²	655	±5%
Caliper	µm	770	±7.5%
Moisture	%	8.0	±0.5%
Smoothness µm	ISO8791-4	-	<2.0 µm
Stiffness CD	(50mm/5° - DIN53121)	900	-15%
Stiffness MD	(50mm/5° - DIN53121)	450	-15%
ISO brightness +UV	ISO2470	95%	±3%

Tolerances, when specified, are based on 95% confidence limits on single mill measurements of random samples measured in manufacturing conditions. Indicative technical values (23°C RH 50%).

Issued 01.04.2017.



SPEYPACK